



## AR2006 DATA SHEET

### Aluminium Pressure Profiles

- Mill Finished
- Easy onsite installation
- Profile length: 3 m



### Aluminium Alloy 6063.T5 Chemical Properties

	Si	Fe	Cu	Mn	Mg	Zn	Ti	Cr
Standard of 6063T5	0.20 - 0.60	Max 0.35	Max 0.10	Max 0.10	0.45 - 0.90	Max 0.10	Max 0.10	Max 0.10

### Aluminium Alloy 6063.T5 Physical Properties

Property	Value
Density	2.70 Kg/m <sup>3</sup>
Melting Point	600 °C
Thermal Expansion	23.5 x 10 <sup>-6</sup> /K
Modulus of Elasticity	69.5 GPa
Thermal Conductivity	200W/m.K
Electrical Resistivity	0.035 x 10 <sup>-6</sup> Ω .m

